

I.1. Scientific Report (Summary)
regarding the implementation of the project throughout the period of execution
(September 2013 – September 2016)

Project PN-II-ID-PCE-2012-4-0470
„Interphase Exchange Coupling in Hard/Soft Magnetic Nanocomposites”

In the following we will present a **summary** of the *Scientific Report* regarding the *implementation of the project (September 2013 – September 2016)*

Contents of the Extended Report

I.	Project Objectives.....	3
I.1.	Specific Objectives of the 2013 Phase.....	3
I.2.	Specific Objectives of the 2014 Phase.....	3
I.3.	Specific Objectives of the 2015 Phase.....	3
I.4.	Specific Objectives of the 2016 Phase.....	4
II.	Summary	4
II.1.	Phase 1 Summary (September 2013 – December 2013).....	4
II.2.	Phase 2 Summary (December 2013 – December 2014).....	5
II.3.	Phase 3 Summary (16/12/2014 — 31/12/2015).....	6
II.4.	Phase 4 Summary (01/01/2016 — 30/09/2016).....	7
III.	Description of Scientific Results and Accomplishment of Project Objectives	9
III.1.	Summary of the Results Obtained in Phases 1 and 2 (September 2013 - December 2014) ...	9
III.1.1	References for the Period September 2013 - December 2014.	10
III.2.	Summary of the Results Obtained in <i>Phase 3 (December 2014 – December 2015)</i>	13
III.2.1	Influence of Al on the Magnetic Properties of the TmCo ₄ Al Intermetallic Compound [1]	13
III.2.2	Magnetic Behaviour of the Ce-Co-Mn Intermetallics with a MgCu ₂ Structure Type [2]	16
III.2.3	Effect of Ni Doping on the Structural, Electronic and Magnetic Properties of the Mn ₅₀ Al ₅₀ Alloy [3-5]	17
III.2.4	Structural, Magnetic and Electronic Properties of Intermetallic Compounds From the Ce-Co-Mn System [6]	25
III.2.5	Influence of Milling and Annealing Conditions on the Structure, Microstructure, and Interphase Exchange Coupling in Nd ₂ Fe ₁₄ B/ α -Fe Magnetic Nanocomposites [7-11]	27
III.2.6	Conclusions and Perspectives_Phase 3/2015.....	39

III.3. Summary of the Results Obtained in <i>Phase 4 (January 2016 – September 2016)</i>	42
III.3.1 Influence of Microstructure on the Interphase Exchange Coupling of Nd ₂ Fe ₁₄ B+10wt% α -Fe Nanocomposites Obtained at Different Milling Energies [39-42].	42
III.3.2 Effect of Starting Powder Premixing on the Interphase Exchange Coupling in Nd ₂ Fe ₁₄ B+10wt%Fe Nanocomposites Obtained Trough Mechanical Milling [43, 44].	46
III.3.3 The Influence of Short Time Heat Treatment on the Microstructure and Magnetic Behavior of the SmCo ₅ / α -Fe Nanocomposite Obtained by Mechanical Milling [45].	51
III.3.4 Study of the Structural, Electronic and Magnetic Properties of New Rare Earth Free Hard Magnetic Phases [46-49].	54
III.3.5 Local electron-electron interaction strength in ferromagnetic nickel determined by spin- polarized positron annihilation [50].	59
III.3.6 Conclusions_Phase 4/2016	59
References	61

I. Project Objectives

1. The first objective focuses on the elaboration and study of ***new hard and soft magnetic phases*** with remarkable magnetic properties, aiming to optimize the interphase exchange coupling, resulting in exchange coupled magnets, spring magnets, with high remanence and coercivity. This objective will be fulfilled by 3 work packages.
2. The second objective, the main objective of the project, aims at developing ***exchange coupled hard/soft magnetic nanocomposites*** with a high energy product, obtained through mechanical milling or quenching, using hard phases such as SmCo₅, Nd₂Fe₁₄B, Sm₂Fe₁₇N_x or the newly obtained hard phases and soft phases based on Fe or Fe-Co alloys. The interphase exchange coupling leads to the whole composite behaving like a single hard magnetic phase. This objective will be fulfilled by another 3 work packages.

I.1. Specific Objectives of the 2013 Phase

1. Soft magnetic phases with high magnetization values.
2. Hard magnetic phases with low rare earth content of the *R-M-A* type (*R* = rare earth, *M* = 3d transition metal, *A* = metalloid) with high anisotropy and coercivity.

3. Hard/soft nanocomposites with good coercivity and with remanence values higher than those of the hard phases.

I.2. Specific Objectives of the 2014 Phase

1. Hard magnetic phases with low or no rare earth content with high anisotropy and magnetization.
2. The study of the strength of the interphase exchange coupling as a function of the composition, structure and microstructure of the magnetic nanocomposites.
3. Project management and acquisition of materials and equipment.

I.3. Specific Objectives of the 2015 Phase

1. New hard magnetic phases based on 3d transition metals with strong anisotropy and high magnetization.
2. Hard/soft interphase exchange coupling: theoretical estimations and experimental confirmation. Spring magnets with high coercivity and high remanence resulting from the improving the interphase exchange coupling.
3. Project management and acquisition of materials and equipment.

I.4. Specific Objectives of the 2016 Phase

1. Spring magnet nanocomposites obtained by mechanical milling or rapid quenching with good coercivity and exchange enhanced remanence.
2. Project management and acquisition of materials and equipment.

II. Summary

II.1. Phase 1 Summary (September 2013 – December 2013)

As we have shown in the project proposal, some of the research contained in this project is performed in collaboration with our national or international partners. Even though the financing of the project started in September 2013, thanks to the support of our European partners (University of Rouen and Louis Néel Institute in Grenoble) we have managed to start the research work earlier, and as a result, the obtained results were already presented at international conferences and workshops or published in scientific journals [17, 22, 23, 37]. Furthermore, a PhD thesis on the project topic was finalized on December 19th 2013 [1]. Starting from the assumed objectives and proposed research activities, the studies performed

during the project phase correspond to the objectives of the first phase and can be summarized as follows:

- The elaboration of new hard magnetic phases of the $R\text{-Co-}M$ type (R = rare earth, M = transition metal) and MnAl alloys doped with Ni. The structural and magnetic characterization along with the study of the influence of metalloid and Ni doping, respectively, on the electronic structure [1].
- Effect of milling and annealing conditions on the crystallographic, morphological and magnetic properties of exchange-coupled nanocomposite of the $\text{SmCo}_5/(\text{Fe}$ or $\text{Fe}_{65}\text{Co}_{35})$ and $\text{Nd}_2\text{Fe}_{14}\text{B}/\alpha\text{-Fe}$ type [17, 22, 23, 37].
- The investigation of different milling types, milling energies and sample preparation on the interphase exchange coupling [17, 22, 23, 37].

II.2. Phase 2 Summary (December 2013 - December 2014)

Following the assumed objectives, the performed research was focused on studying new hard magnetic phases with low or no rare earth content with high anisotropy and magnetization values and the optimization of the interphase exchange coupling as a function of the composition, structure and microstructure of the nanocomposites. The results can be summarized as follows:

- the study of new magnetic phases $R\text{Co}_{5-x}M_x$ type (R = Pr, Sm, Tb, Er și Tm; M = Si, Ge, Al, Ga; x = 0,5 și x = 1): the elaboration of the compounds, the study of the crystal structure by X-ray (XRD) and neutron diffraction, the study of the electronic structure by XPS, magnetic measurement studies and the study of the magnetic structure through neutron diffraction.
- the elaboration and study of new hard magnetic phases without rare earths of the MnAl type doped with Ni, Ti and Zn: the preparation of the alloys, the study of the magnetic τ -phase stability as a function of composition and preparation (arc and induction melting, quenching, slow cooling) and annealing conditions through XRD, differential thermal analysis and thermomagnetic measurements and the theoretical study of the electronic structure and the determination of the crystallographic positions occupied by the dopant elements: Ni, Ti or Zn.
- In order to determine the influence mechanisms of structure, microstructure and morphology on the interphase exchange coupling in hard/soft exchange coupled nanocomposites, we studied the effect of milling and annealing conditions on the

structure and microstructure as well as on the magnetic behavior of the studied nanocomposites as a whole. The milling energy was varied in two ways: a) by modifying the dimension of the milling balls and b) different milling times. The structure and microstructure of the nanocomposite powders was controlled by two annealing types: a) classical annealing at a temperature of 450-650 °C for 0.5-10 h and b) short time annealing at temperatures of 700, 750 or 800°C for 0.5-3 minutes.

- Theoretical calculations were focused on the elaboration of models which could be applied for Bloch or Néel wall movement in magnetic materials. On the other hand, density functional theory calculations in the LSDA+DMFT approximations played an important role in describing the electronic structure of 3d transition metals, the dynamic correlations (by means of LSDA+DMFT) determining larger relativistic corrections.

The obtained results were presented at international conferences (invited lectures, oral and poster presentations) [8, 9, 11, 24-27] and published in scientific journals [2, 3, 5, 6, 7, 10, 41].

References for Phases 1 and 2 (September 2013 - December 2014)

1. Ancuța Laslo, *"Structural and Magnetic Properties of Intermetallic Compounds based on Rare Earths, Cobalt and Metalloids"*, joint PhD thesis, Babeș-Bolyai University/Joseph Fourier University, defended on December 19th 2013.
2. A.Laslo, R.Dudric, M.Neumann, O.Isnard, M.Coldea, V.Pop, Solid State Commun. 199 (2014) 43–46.
3. A. Laslo, V. Pop, O. Isnard, J. Alloys Compd. 626 (2015) 70-75.
4. G. Garreau, V.Schorsch, E.Beaurepaire, J.C.Parlebas, O.Speder, P.Rennert, J. Phys. IV Colloq. C9 4(1994) 127–130.
5. L. Chioncel, D. Benea, S. Mankovsky, H. Ebert, and J. Minar, Phys. Rev B 90 (2014) 184426
6. L. Chioncel, D. Benea, H. Ebert, I. Di Marco, and J. Minar, Phys. Rev B 89 (2014) 094425
7. S. Mican, R. C. Gavrea, B. V. Neamțu, M. Coldea and V. Pop, Studia Univ. "Babes-Bolyai", Physica, 59 nr. 1 (2014) 83-90.
8. S. Mican, D. Benea, V. Pop, O. Isnard and M. Coldea, *"Electronic and Magnetic Properties of $Mn_{50}Al_{46}M_4$ ($M = Mn, Ni, Ti$) Alloys"*, IEEE International Magnetism Conference INTERMAG Dresden 2014, poster presentation.
9. R. Gavrea, S. Mican, D. Benea, B.Neamțu, M. Coldea and V. Pop, *Structural and Magnetic Properties of the $Mn_{50}Al_{46}M_4$ Alloy*, The 14th International Balkan Workshop on Applied Physics, IBWAP Constanța 2014, poster presentation.
10. D. Benea, S. Mican, M. Coldea and V. Pop, Studia Univ. "Babes-Bolyai", Physica, 59 nr. 1 (2014) 7-12

11. V. Pop, *Recent Development of Rare Earth Lean Permanent Magnets*, The 14th International Balkan Workshop on Applied Physics, IBWAP Constanța 2014, *invited lecture*.
12. H. Kono, J. Phys. Soc. Jpn., 13 (1958) 1444.
13. T. E. Prost, Thesis: *Magnetic Properties Study of the Mn-Al System with Additions of B or C and Mechanical Milling Techniques*, University of Nebraska- Lincoln (2012).
14. Z. W. Liu et al., J. Mat. Sci. 47 (2012) 2333-2338.
15. H. Ebert et al., Rep. Prog. Phys. 74 096501 (2011).
16. H.X. Wang et al, Open J. of Microphysics 1 (2011) 19.
17. E. Dorolti, A. V. Trifu, O. Isnard, I. Chicinaș, F. Tolea, M. Valeanu and **V. Pop**, *"Influence of Mechanical Milling on the Physical Properties of SmCo₅/Fe₆₅Co₃₅ type Hard/Soft Magnetic Nanocomposite"*, J. Alloys Compd. 560 (2013) 189-194.
18. N. Poudyal, C. Rong, Y. Zhang, D. Wang, M. J. Kramer, R. J. Herbert and J. P. Liu, J. Alloys Compd. 521 (2012) 55–59.
19. M. Hansen and K. Anderko, *Constitution of Binary Alloys*, McGrawHill, 1958.
20. M. Ito, K. Majima, T. Umemoto, S. Katsuyama and H. Nagai, J. Alloys Compd. 329 (2001) 272–277.
21. Ya. G. Bogatin and E. G. Povolotskii, Sov. Powder Metall. Met. Ceram. 20 (1981) 60.
22. **V. Pop**, O. Isnard and I. Chicinaș, *"The Influence of Milling and Annealing Conditions on the Structural and Magnetic Behaviour of Hard/Soft Magnetic Nanocomposite"*, Invited lecture at „Energy and Materials Criticality Workshop, Santorini 2013”.
23. **V. Pop**, O. Isnard and I. Chicinaș, *"Structural and Magnetic Properties of Nd₂Fe₁₄B/ α -Fe Milled Nanocomposites"*, oral presentation at „International Conference on Sciences, 8-9 November 2013 Oradea”.
24. V. Pop, S. Mican, L. V. B. Diop, I. Chicinaș and O. Isnard, *"Microstructure and Interphase Magnetic Coupling in Nd₂Fe₁₄B/ α -Fe Nanocomposites Obtained by Mechanical Milling and Short Time Annealing"*, IEEE International Magnetism Conference INTERMAG Dresden 2014, poster presentation.
25. V. Pop, S. Mican, O. Isnard, I. Chicinas, *"Propriétés magnétiques et structurales des nanocomposites magnétiques Nd₂Fe₁₄B/ α -Fe obtenus par broyage mécanique de haute énergie"*, Matériaux 2014, Montpellier, *oral presentation*.
26. S. Mican, R. Hirian, V. Pop, I. Chicinaș and O. Isnard, *Structural and Magnetic Properties of Nd₂Fe₁₄B/ α -Fe Nanocomposites Obtained by Mechanical Milling and Short Time Annealing*, The 14th International Balkan Workshop on Applied Physics, IBWAP Constanța 2014, poster presentation.
27. S. Mican, R. Hirian, O. Isnard, I. Chicinaș, V. Pop, *Effect of Milling and Annealing Conditions on the Interphase Exchange Coupling of Nd₂Fe₁₄B/ α -Fe Magnetic Nanocomposites*, oral presentation/Proceedings of the 23rd International Workshop on Rare Earth and Future Permanent Magnets and Their Applications (REPM2014), Annapolis USA 2014, p 415-417
28. P. Saravanan, R. Gopalan, D. Sivaprahasam and V. Chandrasekaran, Intermetallics 17 (2009) 517.
29. S. Y. Zhang, H. Xu, J. S. Ni, H. L. Wang, X. L. Hou and Y. D. Dong, Physica B 393 (2007) 153.
30. J. Bernardi, T. Schrefl, J. Fidler, Th. Rijk, K. de Kort, V. Archambault, D. PeHreH, S. David, D. Givord, J. F. O'Sullivan, P. A. I. Smith, J. M. D. Coey, U. Czernik and M. GroK nefeld, J. Magn. Magn. Matter. 219 (2000) 186.
31. H. W. Chang, Y. T. Cheng, C. C. Hsieh, W. C. Chang and A. C. Sun, J. Alloys Compd. 509 (2011) 1249.

32. D. W. Hu, M. Yue, J. H. Zuo, R. Pan, D. T. Zhang, W. Q. Liu, J. X. Zhang, Z. H. Guo and W. Li, *J. Alloys Compd.*, 538 (2012) 173.
33. B. Balamurugan, D.J. Sellmyer, G.C. Hadjipanayis and R. Skomski, *Scripta Mater.* **67**(2012) 542.
34. R. Skomski, P. Manchanda, P. Kumar, B. Balamurugan, A. Kashyap, D. J. Sellmyer *IEEE Trans. Magn* **49**(2013) 3215.
35. L. Zheng, B. Cui and G. C. Hadjipanayis, *Acta Materialia* 59 (2011) 6772–6782.
36. S. Zhang, H. Xu, X. Tan, J. Ni, X. Hou and Y. Dong, *SJ. Alloys Compd.* 459 (2008) 41.
37. R. Lardé, J-M. Le Breton, A. Maître, D. Ledue, O. Isnard, **V. Pop** and I. Chicinaş, *Atomic Scale Investigation of SmCo₅/α-Fe Nanocomposites: Influence of Fe/Co Interdiffusion on the Magnetic Properties*. *J. Phys. Chem. C*, 117(2013) 7801.
38. P. Scherrer *Göttinger Nachrichten Gesell.* **2** (1918)98
39. V. Pop, S. Gutoiu, E. Dorolti, O. Isnard and I. Chicinaş, *J. Alloys Compd.*, **509**(2011) 9964
40. S. Gutoiu, E. Dorolti, O. Isnard, I. Chicinaş, and V. Pop, *J. Optoelectron. Adv. Mater.*, **12**(2010) 2126.
41. B. Tyukodi, Y. Bréchet, and Z. Néda, *Phys. Rev E* 90 (2014) 052404
42. **V. Pop**, O. Isnard, I. Chicinaş, D. Givord and J. M. Le Breton, *J. Optoelectron. Adv. Mater.* 8 (2006) 494.
43. J. M. Le Breton, R. Lardé, H. Chiron, **V. Pop**, D. Givord, O. Isnard and I Chicinaş, *J. Phys. D: Appl. Phys.* 43 (2010) 085001.

II.3. Phase 3 Summary (16/12/2014 — 31/12/2015)

Considering the three phase objectives, the research was focused on the preparation of new hard magnetic phases and the study of their physical properties as well as on the development of new exchange coupled nanocomposites and the study of their structure, microstructure, and magnetic properties - interphase exchange coupling, remanence, coercivity, and maximum energy product. The third objective was accomplished by ensuring the necessary research management (the team comprises students, Master students, PhD students, technicians, researchers, and teaching staff) and by the acquisition of materials and equipment necessary for the implementation of the project. The scientific results of the present phase can be summarized by looking at the two main research objectives of the project, the third objective referring to project management.

The study of new hard magnetic phases with potential applications in spring magnet-type nanocomposite materials was envisaged. For this objective, two classes of compounds were studied:

- ❖ Intermetallic compounds based on the CaCu₅ crystal structure. The substitution of Co with Al in TmCo₅ leads to a partial replacement of Co 3g in the CaCu₅ crystal structure. TmCo₄Al is ferrimagnetically ordered having a Curie temperature of 511 K. Due to the different vicinities of Co, the magnetic moments of Co atoms situated on the two

distinct crystallographic positions are different. At 2 K, TmCo₄Al shows a strong coercivity, $H_c=2,48$ T.

- ❖ Mn-Al-type or Ce-Co-Mn-type alloys and intermetallic compounds based on Mn. The partial substitution of Co with Mn in CeCo₂ preserves the MgCu₂-type structure. Ce and Co do not have magnetic moments in these compounds. The magnetic behavior of CeCoMn, Ce₃Co₃Mn₄ and Ce₃Co₆Mn is determined mainly by the Mn-Mn interactions. The sign of the magnetic coupling between the Mn ions is dependent on the critical Mn-Mn distance of 2.8 Å: $d_{\text{Mn-Mn}} < d_{\text{crit}}$ = antiferromagnetic coupling, $d_{\text{Mn-Mn}} > d_{\text{crit}}$ = ferromagnetic coupling. Ce shows an intermediary valence value in Ce₂Co₁₅Mn₃, CeCo₇Mn₅ and CeCo₈Mn₄, where Co and Mn are magnetic. The substitution of Co with Mn leads to a decrease of the ferromagnetic interactions (Co-Co) and the increase of the antiferromagnetic ones (Co-Mn and Mn-Mn). We have shown that Ce₃Co₆Mn has a paramagnetic behavior in the temperature range 4 - 550 K. The Mn₅₄Al₄₆ and Mn₅₀Al₄₆Ni₄ alloys are polyphase, the magnetic τ phase being favored by thermal treatments at 470°C, the maximum τ phase concentration values being 76 wt.% and 74 wt.% for Mn₅₄Al₄₆ and Mn₅₀Al₄₆Ni₄ respectively. Mn₅₀Al₄₆Ni₄ alloys show the presence of the soft magnetic κ phase which has a lower Curie temperature than the hard magnetic τ phase. The spontaneous magnetizations at 4 K are 112 and 106 Am²/kg for Mn₅₄Al₄₆ and Mn₅₀Al₄₆Ni₄ respectively, given by the Mn magnetic moments of 1,11 μ_B /f.u. and 0,92 μ_B /f.u. respectively. Band structure calculations have shown a preference for Ni to occupy the 1a and 1c Mn positions. The calculated Mn moments were 1,12 μ_B /f.u. and 0,95 μ_B /f.u. respectively, in good agreement with the experimental data. It was shown that the Ni for Mn substitution up to 4 % does not lead to essential changes for the exchange interactions in this system. Milled samples show higher coercivities than bulk ones.

The second objective of the 2015 phase focuses on the soft/hard exchange coupling in Nd₂Fe₁₄B/ α -Fe nanocomposites. We aimed to optimize the interphase exchange coupling in order to obtain spring magnets with high coercivity, remanence and energy product:

- ❖ (Nd,Dy)₂Fe₁₄B/ α -Fe nanocomposites with 10 or 22 wt.% α -Fe were prepared by mechanical milling and **two types of thermal treatments** - classical annealing (550 °C for 1.5 h) and short time annealing at high temperatures of 700-800 °C for times shorter than 3 min. The structure, microstructure and strength of the interphase exchange coupling were experimentally modeled using the milling conditions and the two annealing types. The X-ray diffraction patterns and homogeneity of the chemical

composition of the sample particles shows a good homogeneity of the two magnetic phases at the nanometer level. The best magnetic properties were obtained for samples milled for 6 or 8 h. Short time annealing leads to a better crystallinity of the Nd₂Fe₁₄B hard phase and a hampered growth of the Fe crystallites. For all of the composites, the samples with 10 wt.% Fe show the best magnetic properties.

- ❖ We have shown the *importance of milling geometry* (bowls with Ø = 10 mm or Ø = 15 mm size balls) on the physical properties of Nd₂Fe₁₄B+10 wt% Fe nanocomposites. Due to its reduced effect on the crystallinity of the hard Nd₂Fe₁₄B, milling with larger diameter balls leads to higher coercivities. This conclusion was based on the comparison of XRD and magnetic data. It was shown that the Fe crystallite sizes can be kept in the 5-20 nm range, dimensions which favor a good hard/soft exchange coupling. Coercive fields up to 0.65 T were obtained, with remanence values of 110 Am²/kg and (BH)_{max} values of 127 kJ/m³. The optimization of the magnetic behavior (coercivity, remanence and rectangularity of the demagnetization curve) was discussed taking into account the structure and microstructure of the composite.

The obtained scientific results were presented at international conferences and summer schools (invited lectures, oral or poster presentations) [4, 5, 9-11] and published in scientific journals [1-3, 6-8].

II.4. Phase 4 Summary (01/01/2015 — 30/09/2016)

Starting from the assumed phase objectives we focused our attention on two priority research directions:

- The synthesis of new exchange coupled magnetic nanocomposites and the study of their structure, microstructure and magnetic properties: interphase exchange coupling, remanence, coercivity, and maximum specific energy [39-45].
- The synthesis of new rare earth free magnetic phases. We focused on a fundamental study of the structural, electronic, and magnetic properties, as well as the potential applications of these new magnetic phases [46-49].

The objective regarding the project management, materials and equipment acquisitions was fulfilled by providing the necessary research management (the project team is comprised of students, master students, PhD students, technicians and academic staff) and through the acquisition of equipment and materials necessary for the project activities.

The scientific results of the actual phase can be summarized as follows:

- Different milling energies were obtained by milling with balls having different diameters between 5 and 20 mm. The crystallites of the hard magnetic phase decrease in size with increasing impact energy. The total milling energy was not found to be a critical parameter. The interphase exchange coupling strength increases with decreasing crystallite size, however, saturation is not reached. We concluded that milling with 15-20 mm diameter balls leads to the best magnetic properties.
- The initial homogenization of the starting powder mixture leads to better magnetic properties.
- Using premilled Fe powders leads to smaller Fe crystallite sizes in the nanocomposite; however, it does not lead to an improvement of the magnetic properties due to the negative influence on the crystallinity of the hard magnetic phase.
- Short time annealing led to significant improvements of the magnetic properties in $\text{Nd}_2\text{Fe}_{14}\text{B}/\alpha\text{-Fe}$ nanocomposites, however, in $\text{SmCo}_5/\alpha\text{-Fe}$ nanocomposites this behavior was not observed.
- Band structure calculations showed a preference for Ti to occupy the Al crystallographic positions in $\text{Mn}_{54-x}\text{Al}_{46}\text{Ti}_x$. The presence of Ti leads to an increase in magnetization and Curie temperature, a behavior which was attributed to the decrease of the antiferromagnetic interactions in the system.
- Preliminary theoretical results in the Fe-N system showed an increase of $\alpha''\text{-Fe}_{16}\text{N}_2$ phase stability for substitutions of Fe with small quantities of Ti or Zr.

The scientific results were presented at international conferences or summer schools (invited lectures, oral presentations or posters) [39, 40, 42, 43, 45, 47-49] and published in scientific journals [41, 44, 46, 50].

The two PhD students involved in the project presented oral and poster presentations at two workshops, one summer school, and two scientific conferences. Also, one master student and three bachelor students worked on the project thematic for their bachelor and dissertation theses.

III. Conclusions and Perspectives

III.1. Phases 1 and 2 _September 2013 - December 2014.

The research work performed in the two phases, presented in detail in the Chapter III of the Extended Scientific Report for the period September 2013 - December 2014 show that

the objectives of these phases were accomplished. A PhD thesis was finalized and defended, the subject being in good agreement with the project objectives regarding the elaboration and study of new hard magnetic phases. The research was focused on the study of new magnetic phases of the $R\text{Co}_{5-x}M_x$ type, the elaboration of the alloys, the study of the crystal structure by XRD and neutron diffraction, the study of the electronic structure through XPS and band structure calculation, magnetic measurement studies and the study of the magnetic structure through neutron diffraction.

The study of new hard magnetic phases without rare earths was undertaken, the research being focused on MnAl-type phases. In order to accomplish this task the crystallographic stability and magnetic properties of the parent $\text{Mn}_{50}\text{Al}_{50}$ and the phases doped with Mn, Ni, Ti or Zn were determined through electronic structure calculations. Experimental studies have shown that the partial substitution of Al with Ni leads to the formation of a second magnetic phase different than the metastable τ phase. We published results obtained on nanocomposites containing soft phases with high magnetization values, such as $\text{Fe}_{65}\text{Co}_{35}$.

Different milling types were performed in order to optimize the microstructure of the nanocomposites: wet and dry milling, milling at variable energies and shock and friction milling. Regarding the annealing method, two annealing types were chosen: a) a classical annealing for long times at temperatures lower than the recrystallization temperature of the soft phases and b) short time annealing at temperatures higher than the recrystallization temperatures of the hard phases. The magnetic properties of the nanocomposites were studied as a function of the structure and microstructure of the nanocomposite, being one of the main project tasks regarding the enhancement of the interphase exchange coupling. Atom probe tomography gave precious information regarding the interphase diffusion and the evolution of phase composition at the interface. In collaboration with our colleagues at the University of Rouen, for the microstructure and interphase coupling studies on the new hard/soft nanocomposites, we will pay special attention to this research in the next phases. In this sense, for a better understanding and use of interphase diffusion, atom probe tomography studies on short time annealed nanocomposites will be a priority.

Theoretical calculations were focused on the elaboration of models which could be applied for Bloch or Néel wall movement in magnetic materials. On the other hand, density functional theory calculations in the LSDA+DMFT approximations played an important role in describing the electronic structure of $3d$ transition metals, the dynamic correlations (by means of LSDA+DMFT) determining larger relativistic corrections.

III.2. Phase 3 _16/12/2014 - 31/12/2015

The summary of the research results shown in Chapter III of the *Extended Scientific Report* for the period September 2013 - December 2015 has shown that the objectives for this time period have been accomplished. After the finalization of a PhD thesis in 2014, in 2015 a PhD thesis was continued and a new one was started in October 2015. During this phase we focused on the study of new hard magnetic phases with applications in spring magnet-type nanocomposite materials. For this we studied two classes of compounds:

- Intermetallic compounds based on the CaCu_5 crystal structure
- Mn-Al or Ce-Co-Mn-type alloys and intermetallic compounds based on Mn.

The second objective was focused on the study of the hard/soft exchange coupling in $\text{Nd}_2\text{Fe}_{14}\text{B}/\alpha\text{-Fe}$ nanocomposites, where we aimed to optimize the interphase exchange coupling in order to obtain spring magnet materials with high coercivity, remanence and energy product.

The substitution of Co with Al in TmCo_5 lead to the substitution of Co 3g in the CaCu_5 crystal structure. TmCo_4Al is ferrimagnetically ordered, having a Curie temperature of 511 K. Due to the different vicinities of Co, the Co magnetic moments on the two distinct crystallographic positions are different. At 2 K, TmCo_4Al shows a high coercivity, $H_c=2,48$ T.

The partial substitution of Co with Mn in CeCo_2 preserves the MgCu_2 -type structure. Ce and Co do not have magnetic moments in these compounds. The magnetic behavior of CeCoMn , $\text{Ce}_3\text{Co}_3\text{Mn}_4$ and $\text{Ce}_3\text{Co}_6\text{Mn}$ is determined mainly by the Mn-Mn interactions. The sign of the magnetic coupling between the Mn ions is dependent on the critical Mn-Mn distance of 2.8 Å: $d_{\text{Mn-Mn}} < d_{\text{crit}}$ = antiferromagnetic coupling, $d_{\text{Mn-Mn}} > d_{\text{crit}}$ = ferromagnetic coupling. Ce shows an intermediary valence value in $\text{Ce}_2\text{Co}_{15}\text{Mn}_3$, CeCo_7Mn_5 and CeCo_8Mn_4 , where Co and Mn are magnetic. The substitution of Co with Mn leads to a decrease of the ferromagnetic interactions (Co-Co) and the increase of the antiferromagnetic ones (Co-Mn and Mn-Mn). We have shown that $\text{Ce}_3\text{Co}_6\text{Mn}$ has a paramagnetic behavior in the temperature range 4 - 550 K.

The $\text{Mn}_{54}\text{Al}_{46}$ and $\text{Mn}_{50}\text{Al}_{46}\text{Ni}_4$ alloys are polyphase, the magnetic τ phase being favored by thermal treatments at 470°C, the maximum τ phase concentration values being 76 wt.% and 74 wt.% for $\text{Mn}_{54}\text{Al}_{46}$ and $\text{Mn}_{50}\text{Al}_{46}\text{Ni}_4$ respectively. $\text{Mn}_{50}\text{Al}_{46}\text{Ni}_4$ alloys show the presence of the soft magnetic κ phase which has a lower Curie temperature than the hard magnetic τ phase. The spontaneous magnetizations at 4 K are 112 and 106 Am^2/kg for

Mn₅₄Al₄₆ and Mn₅₀Al₄₆Ni₄ respectively, given by the Mn magnetic moments of 1.11 μ_B /f.u. and 0.92 μ_B /f.u. respectively. Band structure calculations have shown a preference for Ni to occupy the 1*a* and 1*c* Mn positions. The calculated Mn moments were 1.12 μ_B /f.u. and 0.95 μ_B /f.u. respectively, in good agreement with the experimental data. It was shown that the Ni for Mn substitution up to 4 % does not lead to essential changes for the exchange interactions in this system. Milled samples show higher coercivities than bulk ones.

(Nd,Dy)₂Fe₁₄B/ α -Fe nanocomposites with 10 or 22 wt.% α -Fe were prepared by mechanical milling and two types of thermal treatments - classical annealing (550 °C for 1.5 h) and short time annealing at high temperatures of 700-800 °C for times shorter than 3 min. The structure, microstructure and strength of the interphase exchange coupling were experimentally modeled using the milling conditions and the two annealing types. The X-ray diffraction patterns and homogeneity of the chemical composition of the sample particles shows a good homogeneity of the two magnetic phases at the nanometer level. The best magnetic properties were obtained for samples milled for 6 or 8 h. Short time annealing leads to a better crystallinity of the Nd₂Fe₁₄B hard phase and a hampered growth of the Fe crystallites. For all of the composites, the samples with 10 wt.% Fe show the best magnetic properties,

We have shown the importance of milling geometry (bowls with $\varnothing = 10$ mm or $\varnothing = 15$ mm size balls) on the physical properties of Nd₂Fe₁₄B+10 wt% Fe nanocomposites. Due to its reduced effect on the crystallinity of the hard Nd₂Fe₁₄B, milling with larger diameter balls leads to higher coercivities. This conclusion was based on the comparison of XRD and magnetic data. It was shown that the Fe crystallite sizes can be kept in the 5-20 nm range, dimensions which favor a good hard/soft exchange coupling. Coercive fields up to 0.65 T were obtained, with remanence values of 110 Am²/kg and (BH)_{max} values of 127 kJ/m³. The optimization of the magnetic behavior (coercivity, remanence and rectangularity of the demagnetization curve) was discussed taking into account the structure and microstructure of the composite.

Considering that two PhD students are involved in the research activities proposed in this project, the studies in the next time period will be focused on two main directions: the preparation and study of new hard magnetic systems including anisotropic alloys based on Fe and Fe-Co and the second, and most important objective, the optimization of the interphase exchange coupling through the use of new magnetic phases, in order to prepare new spring magnet-type materials with high coercivity and remanence and the fabrication of magnets through Spark Plasma Sintering (SPS).

The research results were published or presented at international scientific conferences. The PhD students involved in the project participated at two summer schools where they presented posters with the obtained results. The project website, <http://www.phys.ubbcluj.ro/~viorel.pop/PN-II-ID-PCE-2012-4-0470/pn2.html>, is updated with all of these results.

III.3. Phase 4 _ 01/01/2016 - 30/09/2016

The research activity for this year were conducted into two main directions:

- Obtaining new exchange coupled magnetic nanocomposites and the study of the structure, microstructure and magnetic properties: interphase exchange coupling, remanent magnetization, coercivity and maximum specific energy.

- Obtaining and study of new magnetic phase without rare earths. We considered a fundamental study of the structural, electronic and magnetic properties and the application potential of these new magnetic phase.

The main conclusions of our researches could be summarized as follows:

Different milling energies have been obtained by mechanical milling with balls of diameters between 5 and 20 mm. Hard magnetic phase crystallite size decreases with increasing impact energy. The total energy milling is not a critical parameter. The crystallite sizes are smaller the interphase exchange coupling is stronger; the saturation of this evolution was not reached. We concluded that milling balls of 15-20 mm lead to the best magnetic properties.

- The good homogenization of the starting powders results in the improving of the magnetic properties.
- The use of pre-milled Fe powder leads to the decreasing the Fe crystallite size of nanocomposite, but do not improve the magnetic properties due to negative influence on the crystallinity of hard magnetic phase.
- If the short time annealing result in a significant improving of the magnetic properties of $\text{Nd}_2\text{Fe}_{14}\text{B}/\alpha\text{-Fe}$ nanocomposite, this effect was not observed in $\text{SmCo}_5/\alpha\text{-Fe}$ nanocomposites.
- Theoretical band structure calculations show a preference of Ti for the crystallographic Al positions in $\text{Mn}_{54-x}\text{Al}_{46}\text{Ti}_x$ alloys. This effect leads to an increase of magnetization and Curie temperature, effect attributed to diminishing strength of the negative magnetic interactions in the system

- Preliminary theoretical studies in Fe-N system show an increase of the stability of α'' -Fe₁₆N₂ phase for small substitution of the Fe with Ti or Zr.

The obtained research results were published in scientific journals or presented at international scientific conferences, workshops and summer schools (invited lectures, oral and poster presentation). The PhD and master students involved in the project participated at two summer schools, two workshops and two scientific conferences where they had oral and posters presentation of the obtained results. The project website, <http://www.phys.ubbcluj.ro/~viorel.pop/PN-II-ID-PCE-2012-4-0470/pn2.html>, is updated with all of these results.

References for Phase 3 and 4, December 2014 - September 2016

1. A. Laslo, V. Pop, O. Isnard „*Influence of Al on the magnetic properties of TmCo₄Al compound, a magnetic and neutron diffraction study*”, J. Alloys Compd. 626 (2015) 70–75.
2. R. Dudric, A. Popescu, O. Isnard, V. Pop and M. Coldea, „*Magnetic Behaviour of the Ce-Co-Mn Intermetallics of MgCu₂ Structure Type*” Acta Phys. Polonica **A128** (2015) 67-71.
3. Sever Mican, DianaBenea, RazvanHirian, RaduGavrea, OlivierIsnard, ViorelPop, Marin Coldea, „*Structural, electronic and magnetic properties of the Mn₅₀Al₄₆Ni₄ alloy*”, J. Magn. Mater. 401 (2016) 841–847.
4. Răzvan Hirian, Diana Benea, Sever Mican, Olivier Isnard, Marin Coldea and Viorel Pop, „*Effect of Ni doping on the Structural, Electronic and Magnetic Properties of the Mn₅₄Al₄₆ Alloy*”, prezentare invitată, NANOPYME Workshop: Rare Earth-Free Permanent Magnets and Applications, 14-16 Sep 2015 - Madrid, Spain.
5. R. Hirian, S. Mican, O. Isnard, I. Chicinaș, M. Coldea and V. Pop, „*Structural and Magnetic Properties of Mechanically Milled Mn₅₀Al₄₆M₄ (M = Mn, Ni) Alloys*”, ICM 2015, Barcelona, Spain.
6. R. Dudric, A. Popescu, O. Isnard, M. Neumann, V. Pop, M. Coldea, „*Structural, Magnetic and Electronic Properties of the Intermetallic Compounds from the Ternary System Ce – Co – Mn*”, Studia Univ. "Babes-Bolyai", Physica, 60 nr. 1 (2015) 21-30.
7. Simona Gutoiu, Olivier Isnard, Ionel Chicinas, Florin Popa, Albert Takacs, Viorel Pop „*The influence of milling and annealing conditions on the structural and magnetic*

- behavior of Nd₂Fe₁₄B/ α -Fe hard/soft magnetic nanocomposites*", J. Alloys Compd. 646 (2015) 859-865
8. Sever Mican, Răzvan Hirian, Olivier Isnard, Ionel Chicinaș, Viorel Pop, „*Effect of Milling Conditions on the Microstructure and Interphase Exchange Coupling of Nd₂Fe₁₄B/ α -Fe Nanocomposites*”, ICM 2015, Physics Procedia dec. 2015, in press.
 9. R. Hirian, S. Mican, I. Chicinaș, O. Isnard, S. Gutoiu and V. Pop, „*Influence of the Synthesis Conditions on the Interphase Exchange Coupling of Nd₂Fe₁₄B/ α -Fe Nanocomposites Obtained by Mechanical Milling*”, PIM 2015, Cluj-Napoca Romania.
 10. R. Hirian, S. Mican, L. V. B. Diop, I. Chicinaș, O. Isnard and V. Pop, „*Influence of Milling Conditions on the Hard/Soft Exchange Coupling of the Short Time Annealed Nd₂Fe₁₄B/ α -Fe Nanocomposite*”, International Summer -School on Physical and Chemical Principles in Materials Science, July 7-16 2015, Xi'An China.
 11. S. Mican, R. Hirian, O. Isnard, I. Chicinaș and V. Pop, „*Effect of Milling Energy on the Interphase Exchange Coupling of Nd₂Fe₁₄B/ α -Fe Nanocomposites*”, ESM 2015, Cluj-Napoca Romania.
 12. C. Chacon, O. Isnard, J. Solid State Chem. 154 (2000) 242–245.
 13. H. Mayot, O. Isnard, Z. Arnold, J. Kamarad, J. Phys. Condens. Matter. 20 (2008) 135207.
 14. C. Zlotea, O. Isnard, J. Magn. Magn. Mater. 242–245 (2002) 832–835.
 15. A. Laslo, C.V. Colin, O. Isnard, J. Appl. Phys. 107 (2010) 09A732.
 16. H. Ido, K. Konno, S.F. Cheng, W.E. Wallace, S.G. Sankar, J. Appl. Phys. 67 (1990), 4638.
 17. R. Lemaire, *Cobalt*, 32 (1966) 132
 18. P. Vilars, L. D. Calvert, in: *Pearson's Handbook of Crystallographic Data for Intermetallic Phases*, second ed., ASM International, Materials Park, OH, 1991.
 19. H. Kono, J. Phys. Soc. Jpn., 13 (1958) 1444.
 20. T. E. Prost, Thesis: *Magnetic Properties Study of the Mn-Al System with Additions of B or C and Mechanical Milling Techniques*, University of Nebraska- Lincoln (2012).
 21. H. Jian, K. P. Skokov, O. Gutfleisch. J. Alloys Compd. 622 (2015) 524-528.
 22. P. Saravanan, V.T.P. Vinod, M. Černík, A. Selvapriya, D. Chakravarty, S.V. Kamat, J. Magn. Magn. Mater. 374 (2015) 427–432.
 23. I. Tsuboya, M. Sugihara, J. Phys. Soc. Jpn. 16 (1961) 1257. I. Tsuboya, M. Sugihara, J. Phys. Soc. Jpn. 17 (Supplement B1) (1962) S172.
 24. Liu Z W et al., J. Mat. Sci. 47 (2011) 2333.

25. J.G. Booth, H.P.J. Wijn, G. Zibold, Landolt-Bornstein Numerical Data and Functional Relationships in Science and Technology, 19, Springer-Verlag, Germany (1987), p. 287–288.
26. J. H. Park, Y. K. Hong, S. Bae, J. J. Lee, J. Jalli, G. S. Abo, N. Neveu, S. G. Kim, C. J. Choi and J. G. Lee, *Journal of Applied Physics*, 107, 09A731, 2010.
27. H. Nakamura, K. Yoshimoto, M. Shiga, M. Nishi, K. Kakurai, *J. Phys.: Condens. Matter* 9 (1997) 4701–4728.
28. J.C. Fuggle, F.U. Hillebrecht, Z. Zolnierrek, R. Läser, Ch. Freiburg, O. Gunnarsson, K. Schönhammer, *Phys. Rev. B*, 27, 7330 (1983).
29. Y. Baer, Ch. Zürcher, *Phys. Rev. Lett.*, 39, 956 (1977).
30. M. Coldea, M. Neumann, St. Lütkehoff, S. Mähl, R. Coldea, *J. Alloys Compd.*, 278, 72 (1998).
31. S. Hüfner, *Photoelectron Spectroscopy Principles and Applications*, Springer Verlag, Berlin, 1995.
32. P.D. Johnson, Y. Liu, Z. Xu, D.J. Huang, *J. Electron. Spectrosc. Relat. Phenom.*, 75, 245 (1995).
33. G. Garreau, V. Schorsch, E. Beaupaire, J.C. Parlebas, O. Speder, P. Rennert, *J. Phys. IV Colloque C9. 4*, 127 (1994).
34. P. Scherrer, *Göttinger Nachrichten Gesell.* 2 (1918) 98-100.
35. V. Pop, S. Gutoiu, E. Dorolti, O. Isnard and I. Chicinaş, *J. Alloys Compd.*, 509 (2011) 9964.
36. J. Coey, *IEEE Transactions on Magnetism*, 47 (2011) 4671-4681.
37. J. Zhang, S.-y. Zhang, H.-w. Zhang and B.-g. Shen, *J. Appl. Phys.*, 89 (2001) 5601-5605.
38. A. M. Gabay, G. C. Hadjipanayis, M. Marinescu and J. F. Liu, *J. Appl. Phys.*, 107 (2010) 09A704.
39. V. Pop, „*Hard Magnetic Materials with Reduced Rare-Earth Content*”, International Workshop of Materials Physics, Institutul National De Cercetare Dezvoltare pentru Fizica Materialelor, Măgurele 23-25 Mai 2016- prezentare invitată.
40. V. Pop, „*Hard Magnetic Materials for the 21st Century*”, TIM15-16 Physics Conference, Timișoara 26-28 Mai 2016- prezentare invitată.
41. R. Hirian, S. Mican, O. Isnard, L. Barbu-Tudoran and V. Pop „*Influence of Microstructure on the Interphase Exchange Coupling of Nd₂Fe₁₄B+10wt%α-Fe*”

Nanocomposites Obtained at Different Milling Energies". J. Alloys Compd. - in curs de recenzare.

42. R. Hirian, S. Mican, O. Isnard, L. Barbu-Tudoran and V. Pop, „*Influence of Microstructure on the Interphase Exchange Coupling of Nd₂Fe₁₄B+10wt%Fe Nanocomposites Obtained by Mechanical Milling*”. 24th International Workshop on Rare-Earth and Future Permanent Magnets and Their Applications (REPM 16), 28th August - 1st September - Darmstadt, Germany- prezentare poster.
43. R. Hirian, S. Mican, O. Isnard , L. Barbu Tudoran and V. Pop, „*Effect of Starting Powder Premixing on the Interphase Exchange Coupling in Nd₂Fe₁₄B+10wt%Fe Nanocomposites Obtained Trough Mechanical Milling*”. 16th International Balkan Workshop on Applied Physics and Materials Science (IBWAP) 2016, 7th-9th July 2016 - Constanța, Romania-prezentare orală.
44. Sever Mican, Răzvan Hirian, Léopold, V. B. Diopb, Ionel Chicinaș, Olivier Isnard, Viorel Pop, „ *Microstructure and Interphase Magnetic Coupling in Nd₂Fe₁₄B/ α -Fe Nanocomposites Obtained by Mechanical Milling and Short Time Annealing*”, Rom. Journ. Phys., 61 (2016) P. 506–517.
45. R. Hirian, S. Mican, O. Isnard and V. Pop, „*The Influence of Short Time Heat Treatment on the Microstructure and Magnetic Behavior of the SmCo₅/ α -Fe Nanocomposite Obtained by Mechanical Milling*”. 8th Joint European Magnetic Symposia (JEMS), 21st-26th August 2016 - Glasgow, UK- prezentare poster.
46. Radu Gavrea, Răzvan Hirian, Sever Mican, Diana Benea, Olivier Isnard, Marin Coldea and Viorel Pop, „*Structural, electronic and magnetic properties of the Mn_{54-x}Al₄₆Ti_x (x = 2; 4) alloys*”, Intermetallics - in curs de recenzare.
47. R. Gavrea, R.Hirian, S. Mican, D. Benea, O. Isnard, M. Coldea and V. Pop, „*Structural, electronic and magnetic properties of the Mn_{54-x}Al₄₆Ti_x (x=2; 4) alloys*”. 24th International Workshop on Rare-Earth and Future Permanent Magnets and Their Applications (REPM 16), 28th August - 1st September - Darmstadt, Germany- prezentare poster.
48. R. Gavrea, D. Benea, R. Hirian, T. Radu, R. Erhan, M. Coldea and V. Pop, „*The Influence of the Co Doping on the Electronic and Magnetic Properties of the Half-metallic Ferrimagnet Mn₂VAl*”. 11th International Conference on Physics of Advanced Materials (ICPAM), 8th-14th September 2016 - Cluj-Napoca, Romania- prezentare poster.

49. R. A. One, S. Mican, D. Benea and V. Pop, „*Synthesis, structural, electronic and magnetic properties of α'' -(Fe_{1-x}M_x)₁₆N₂ (M = Ti, Zr)*”. 11th International Conference on Physics of Advanced Materials (ICPAM), 8th-14th September 2016 - Cluj-Napoca, Romania- prezentare poster.
50. H. Ceeh, J. A. Weber, P. Böni, M. Leitner, D. Benea, L. Chioncel, H. Ebert, J. Minár, D. Vollhardt and C. Hugenschmidt „*Local electron-electron interaction strength in ferromagnetic nickel determined by spin-polarized positron annihilation*”. Scientific Reports 6 (2016) 20898. <http://dx.doi.org/10.1038/srep20898>.
51. M. Abdellaoui and E. Gaffet, “*The Physics of Mechanical Alloying In a Planetary Ball Mill : Mathematical Treatment*,” Acta. Metall. Mater 43, no. 3 (1995) pp. 1087-1098.
52. O. Boytsov, A. I. Ustinov, E. Gaffet and F. Bernard, "*Correlation Between Milling Parameters and Microstructure*," J. Alloy. Compd. 432 (2007) pp. 103-110.
53. V. Pop, O. Isnard, I. Chicinaş, D. Givord and J. M. Le Breton, „*SmCo₅/α-Fe nanocomposite material obtained by mechanical milling and annealing*”J. Optoelectron. Adv. Mater. 8 (2006) 494.
54. J. M. Le Breton, R. Lardé, H. Chiron, V. Pop, D. Givord, O. Isnard and I Chicinaş, „*A structural investigation of SmCo₅/Fe nanostructured alloys obtained by high-energy ball milling and subsequent annealing*”J. Phys. D: Appl. Phys. 43 (2010) 085001

Project Director,

Prof. dr. Viorel Pop

